# **ALLODERM BLACK 2B**

#### **Drum Pigments**



#### **Chemical Composition**

**Alloderm Black 2B** is non-casein based carbon black pigment grind to very fine particles and disperse in very stable media that would give very good covering and black ness to drum dyed leather.

Leather impregnated with **Alloderm Black 2B** would have very black grain, while the flesh side is grayish and could be remedied by addition of dyestuffs.

### **Application**

- A. Dosage of 1% or more based on shave weight. To achieve best results, it is recommended to add Alloderm Black 2B as topping component. It is important to wash leather properly before any addition of Alloderm Black 2B. Otherwise, optimum yield and exhaustion of Alloderm Black 2B are hard to achieve. (Alloderm Black 2B will not exhaust in floats that have syntans or extracts.)
- **B.** Sandwiching of **Alloderm Black 2B** with Formic Acid is beneficial toward very black leather production.
- C. Alloderm Black 2B will be suitable for dyeing of short naps splits because Alloderm Black 2B will penetrate well without neutralization.
- **D.** For heavy retanned leather, it is advisable to horse up retanned wetblue for at least 18 hours before proceeding with washing fatliquoring and dyeing.

## **Properties**

Appearance: Black Viscous Solution

Analysis: pH 7.0-8.0 Active Ingredient: 37-40%

Density: 1.10-1.20 KG/L

Storage Condition: Optimum Condition is between +5C and +30C.

Keep away from below freezing temperature. Keep in cool and well ventilated warehouse.

Stir well before each application.

Shelf Life: Up to 12 months in the original packing condition.

#### **Packing**

**40KGS Plastic Drums** 

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

Written on 25 August 2016 Product Literature Page 112 of 129